


Formula : C₂₆H₄₂O₄

Molecular Weight : 418.61

CAS Registry Number : 28553-12-0

Abbreviation : DINP(Diisononyl phthalate)

Molecular Structure :



Properties:

Property	Unit	Value	Test method
Dynamic viscosity(20 °C)	mPa·s	50 – 180	ASTM D445
Specific gravity	20 °C/20 °C	0.975±0.003	JIS K-6751
Color	APHA	30 max	JIS K-6751
Refractive index	n _D 25	1.485±0.003	JIS K-6751
Acid value	mg KOH/g	0.03 max	JIS K-6751
Purity	Area %	99.5 min	by gas chromatography
Volatility content	Weight %	0.1 max	JIS K-6751

Description:

DINP is a nearly colorless, clear and practically anhydrous oily liquid. It is soluble in the usual organic solvents like ethyl alcohol, acetone, toluene. DINP is almost insoluble in water. DINP is miscible and compatible with all of the monomeric plasticizers commonly used in PVC. So it can use mixed with the monomeric plasticizers in PVC formulation.

Storage

DINP has an almost unlimited shelf life when properly stored in closed containers at temperatures

hcc.hanwha.co.kr

본사 100-797 서울특별시 중구 장교동 1번지 한화빌딩

The information given herein and other otherwise supplied to users is based on our general experience and where applicable, on the results of tests on samples of typical manufacture. However, because of the many factors which are outside knowledge and control, which can effect the use of these products, users must rely on their own judgment and we cannot accept liability for any injury, loss or damage resulting from reliance upon such information.

below 40 °C and the exclusion of humidity. Always refer to the Material Safety Data Sheet (MSDS) for detailed information on handling and disposal.

Safety and Handling

The Hanwha Solutions Corporation provides its customers with a product specific Material Safety Data Sheet (MSDS) to cover potential health effects, safe handling, use and transportation. Hanwha Solutions Corporation strongly encourage its customers to review MSDS on its products and other materials prior to their use. DINP is normally supplied as a Liquid in 200kg Drum. DINP is not formulated to contain any hazardous or regulated materials such as lead, cadmium, mercury, and chromium compounds. And Hanwha Solutions Corporation guarantee that DINP do not include any hazardous or regulated materials during the manufacturing process.

Properties

Further information and recommendations for processing can be obtained from our technical support staff and representatives. The data and recommendations contained in this brochure represent the current state of our knowledge and serve as a guide only to our products and their potential applications. Therefore, no warranty of specific properties of the products mentioned herein or of their suitability or fitness for a particular purpose is implied. The information given in this brochure should be checked by preliminary trials because of conditions during processing over which we have no control.